

42-3.01D(2) Quality Control

Test for pavement smoothness under sections 36 and 40 except:

1. At the midpoint of a joint or crack, test smoothness with a straightedge.
2. Straightedge and inertial profiler requirements do not apply to areas abnormally depressed from subsidence or other localized causes. End smoothness testing 15 feet before and resume 15 feet after these areas.

After grinding, the existing pavement must comply with specifications for smoothness ~~and coefficient of friction~~ in section 40 except:

1. At the midpoint of a joint or crack, both sides must have uniform texture.
2. Cross-slope must be uniform and have positive drainage across the traveled way and shoulder.

42-3.01D(3) Department Acceptance

The Department accepts pavement for smoothness [under section 40-1.01D](#) and ~~coefficient of friction texture~~ [as described under section 40-1.03H\(3\)](#).